

TEST REPORT n° 1369/12

REGISTER Nr°: 0221/12
PURCHASER: "HEAVY INDUSTRIES shpk" - TIRANE
SAMPLE: TAR SAND (BITUMINOUS SAND)
DATE OF TEST: 19/04/2012
TEST: **DETERMINATION OF BITUMEN CONTENT**
TEST METHOD: CNR B.U. 38


TEST RESULTS

Nr	Description	Unit	Test results
1	Weight of container	g	341.1
2	Weight of sample+container before extraction	g	1477.2
3	Weight of sample+container after extraction	g	1365.0
4	Weight of sample before extraction	g	1136.1
5	Weight of sample after extraction	g	1023.9
6	Weight of bitumen material	g	112.2
7	Bitumen content on total weight	%	9.88
8	Bitumen content on aggregate weight	%	10.96

Note:


TESTED BY

Eng. Rezarta Qemallaj




HEAD OF LABORATORY

Eng. Feim ALLIU



This report belongs only to the sample under the test.
It is forbidden to copy this report or part of it without permission of the lab!!!