


**TEST REPORT n° 1367/12**

REGISTER Nr°: 0221/12  
PURCHASER: "HEAVY INDUSTRIES shpk" - TIRANE  
SAMPLE: TAR SAND (BITUMINOUS SAND)  
DATE OF TEST: 19/04/2012  
TEST: **DETERMINATION OF SIEVE ANALYSIS**  
TEST METHOD: **AASHTO T27**

**TEST RESULTS**

SIEVE (mm)	WEIGHT OF RETAINING MATERIAL (g)	WEIGHT OF RETAINING MATERIAL (%)	PROGRESSIVE PASSING (%)
25.0	0.0	0.0	100.0
19.5	0.0	0.0	100.0
12.5	0.0	0.0	100.0
9.5	0.0	0.0	100.0
4.75	0.0	0.0	100.0
2.00	0.000	0.0	100.0
0.50	1.052	3.6	96.4
0.300	0.696	2.4	94.1
0.150	8.521	28.8	65.3
0.125	9.216	31.2	34.1
0.075	9.454	32.0	2.1
0	0.621	2.1	0.0
TOTAL	29.560	100.0	

**SIEVE ANALYSIS GRAPHIC**



**TESTED BY**

Eng. Rezarta Qemallaj

*[Signature]*

**HEAD OF LABORATORY**

Eng. Feim ALLIU

*[Signature]*

This report belongs only to the sample under the test.  
It is forbidden to copy this report or part of it without permission of the lab!!!



**KIBE 1 LABORATORY**