


TEST REPORT n° 1366/12



REGISTER n°: 0220/12
PURCHASER: "HEAVY INDUSTRIES shpk" - TIRANE
SAMPLE: BITUMINOS MATERIALS
TEST: **SOFTENING POINT AND PENETRATION OF BITUMEN**

TESTI	TEST METHOD	UNITS	RESULTS
Soft Point	ASTM D-36	°C	105.7
Penetration	ASTM D-5-06e1	dmm	0.100
Penetration Index	UNI 4163		-1.22

TESTED BY
Eng. Rezarta Qemallaj



HEAD OF LABORATORY
Eng. Feim Alliu

This report belongs only to the sample under the test.

It is forbidden to copy this report or part of it without permission of the lab!!!